



NC LACQUER TOPCOAT

NC LACQUER TOPCOAT offers excellent mar resistance, cold-check resistance and gloss retention. It is moderately fast drying, and has satisfactory appearance.

INTENDED USE : *For interior use on wooden products*

SPECIFICATIONS

Vehicle Type : *Nitrocellulose and Alkyd Resins.*

Solvents : *Hydrocarbons, ketones, alcohols and esters.*

Specific Gravity : *0.90 ± 0.10*

Solids (by weight) : *35 ± 5%*

Colour : *Clear / Black / White.*
Other colours available upon request.

Theoretical Spreading Rate : *8 – 10 sq. meter / litre @ 40 microns DFT*

APPLICATION

Finishing : *High gloss to matt*

Drying Time : *Dry to touch* 5 – 10 minutes @ 25°C
Dry for sanding / overcoat 20 – 30 minutes @ 25°C
Dry for stacking 2 – 3 hours @ 25°C

Mixing Ratio : *Thin 100 parts of NC Lacquer Topcoat with 100 parts of NC Thinner or until desired viscosity is obtained.*

Clean-up : *NC Thinner*

STORAGE AND CAUTIONS

Shelf Life : *1 year @ 25°C, provided that the product is stored under dry cool condition.*

Cautions : *Contents flammable.*
Keep away from heat, sparks and open flame.
Avoid contact with skin and eyes.
Avoid direct contact with vapour and spray mist.
Use with adequate ventilation.